



CSIRO

## CSIRO Textile and Fibre Technology

Henry St, Belmont, Victoria 3216, Australia.

Telephone: (03) 52464000

Email: [texlab@csiro.au](mailto:texlab@csiro.au)

Fax: (03) 52464057

Web: <http://www.tft.csiro.au>

(ABN: 41 687 119 230)

## Textile Testing Laboratory

### TEST REPORT

Report Number: 05-0782

Page 1 of 1

Date Issued: 12/09/05

Client: DEECOM

Contact: Cam McGregor

Address: 311 Princes Highway  
WERRIBEE VIC 3030

Fax: 03 9742 2877

Sample Description: Green Synthetic Grass

#### Test Method

#### Result

AS 1287

Dimensional Stability to Heat (Modified)

Sample exposed to heat in the form of  
hot air circulating in an enclosed chamber

Temp °C	Length (%Change)	Width (%Change)	Appearance
50	0	0	No change
60	0.8	0.9	No Change
90	-1.2	-0.3	Slight Shrinkage of Pile
100	-1.5	-0.3	Significant Pile Shrinkage Apparent Colour Change

Note: Sample was lying in a flat supported position when tested. Negative result denotes shrinkage

The results contained in this report apply only to the sample submitted to the laboratory. This report must not be reproduced without the written authority of the laboratory and then shall only be reproduced in full.

Approved by:  D.R. Carroll - Laboratory Manager